

CE Data sheet

Rhenofol® CV



Product name:	Rhenofol® CV
Manufacturer/supplier:	FDT FlachdachTechnologie GmbH & Co. KG Eisenbahnstraße 6-8 68199 Mannheim Germany
Production plant:	Mannheim
Type of application:	For sealing mechanically fixed roof build-ups. For the installation, the application guidelines of the manufacturer have to be observed.
FPC certificate no.:	1343-CPD-K060660.6 1343-CPD-K060660.8
FPC issue of certification:	06
European standard:	EN 13956
Product description:	Synthetic PVC-P roofing membrane with internal synthetic fibre reinforcement and not compatible with bitumen.
Standard membrane dimensions:	20 m x 2.05/1.50/1.03/0.68 m x 1.2 mm 20 m x 1.50 m x 1.5 mm 15 m x 2.05/1.03/0.68/0.50 m x 1.5 mm 15 m x 2.05/1.50/1.03 x 1.8 mm 15 m x 1.50 m x 2.0 mm

Rhenofol® CV 1.2–2.0 mm

Properties	EN standard	Results
External fire performance	DIN CEN/TS 1187	B _{roof} (t1) (Testing according DIN CEN/TS 1187 with different roof build-ups. Testing reports can be requested separately.)
Reaction to fire	DIN EN ISO 11925-2 DIN EN 13501-1	class E
Water vapour property μ	DIN EN 1931 (method B)	18,000
Tensile strength	DIN EN 12311-2 (method A)	$\geq 1,000$ N/50 mm
Elongation at break	DIN EN 12311-2 (method A)	$\geq 15\%$
Joint peel resistance	DIN EN 12316-2	≥ 250 N/50 mm
Joint shear resistance	DIN EN 12317-2	≥ 900 N/50 mm (fracture outside the joint area)
Resistance to impact rigid substrate flexible substrate	DIN EN 12691	1.2 mm thickness ≥ 600 mm 1.5 mm thickness ≥ 900 mm 1.8 mm thickness $\geq 1,200$ mm 2.0 mm thickness $\geq 1,800$ mm
Resistance to static load	DIN EN 12730 (method A/B)	≥ 20 kg
Hail resistance rigid substrate flexible substrate	DIN EN 13583	≥ 20 m/s ≥ 30 m/s
Tear resistance	DIN EN 12310-2	≥ 150 N
Dimensional stability	DIN EN 1107-2	$\leq 0.2\%$
Foldability at low temperature	DIN EN 495-5	≤ -30 °C
Chemical resistance	DIN EN 1847 (List annexe C)	passed
UV exposure	DIN EN 1297	class 0 (5,000 h)
Watertightness	DIN EN 1928 (method B)	≥ 400 kPa

FDT legal notice

We refer emphatically to the fact, that all details mentioned, especially the application and utilisation recommendation for the products and their system accessories, have been developed under normal conditions, and based on our knowledge and experience. Appropriate storage and usage of the products are assumed. A warranty or reliability of a finished project cannot be deduced because of varying materials, substrates and differing work conditions, neither by any indications nor from verbal statements, irrespective of any legal positions. For the possible accusation that FDT acted intentionally or grossly negligent, the user has to supply evidence that they provided FDT with all information and details necessary for an appropriate and correct evaluation through FDT in written form, immediately available and complete. The user is responsible for ensuring that the products are suitable for the given application. It is FDT's right to change product specifications without notice. Property rights of third parties are to be considered. In addition our particular sales and delivery terms are valid. The latest version of our product data sheet is obligatory, which can be requested directly through FDT.

All information as well as all technical and drawing data comply with current technical standards and are based on our experience. National standards and regulations must be observed.

Technical changes reserved. As of May 2014. © 2014 FDT FlachdachTechnologie GmbH & Co. KG, Mannheim, Germany

Product information

Rhenofol CV – roofing membrane for mechanically fixed roof build-ups

Rhenofol CV is a product made of non-rigid polyvinyl chloride (PVC-P), not compatible with bitumen, a synthetic fibre reinforced roofing membrane according to DIN EN 13956. Due to the outstanding material characteristics, Rhenofol CV roofing membranes are ideal for single-ply application. Seam overlaps can be easily sealed with solvent or hot-air welding.

Characteristics

- Roofing membrane according to DIN EN 13956
- Weather-resistant
- Resistant to UV radiation
- Resistant to flying sparks and radiant heat according to DIN CEN/TS 1187, confirmed by official test certificates
- Reaction to fire: class E according to DIN EN 13501-1
- Resistant to standard exhaust gas from industrial and heating plants
- Outstanding resistance to natural ageing
- Hail-resistant according to DIN EN 13583
- Thermal conductivity according to DIN 52612: 0.16 W/(m*K)
- Certified with an Environmental Product Declaration (EPD) according to ISO 14025 and EN 15804

Not resistant to:

Bitumen and tar-containing materials; organic solvents such as benzene, toluene, hydrogen chlorides; fats, oils, such as oily cements and forming oils. Not compatible with rigid polystyrene foam.

Quality assurance

Rhenofol CV is subject to constant in-house and external quality control. The in-house quality assurance system for the whole company has been certified according to DIN EN ISO 9001, the world's most strict quality standard, and is constantly monitored by TÜV SÜD Management Service GmbH.

Range of application:

Rhenofol CV is used for waterproofing in mechanically fixed build-ups without ballast, especially for lightweight roofs. Used in conjunction with FDT standing seam profiles a simulated metal welded-seam roof can aesthetically be designed.

**FDT FlachdachTechnologie
GmbH & Co. KG**

Eisenbahnstraße 6-8
68199 Mannheim
Germany

Tel +49 (0) 6 21-85 04-0
Fax +49 (0) 6 21-85 04-2 05
www.fdt.de